

**UPCERA**



# HT WHITE ZIRCONIA

---

Reliable Materials Expert

# HT White



UPCERA HT White, made of 3Y-TZP, is a high translucent zirconia blank used for monolithic or anatomically reduced anterior restorations and framework bridges with porcelain build-up. It offers a good choice of high strength to the labs.

- Ideal for coping and framework
- Ultra-high strength, reduces the fracture risk



Translucency

**39%**




Strength

**1300 MPa**

## Optimum Indications

- Coping
- Reduced posterior bridge ( $\geq 3$  units)

## Sintering program



## Apply for



Open CAD/CAM System,  
Zirkonzahn CAD/CAM System,  
Amann Girrbach CAD/CAM System,  
Cerec in lab (Sirona) System



## Physical Characteristics

Density after sintering	6.08±0.01g/cm <sup>3</sup>
CTE(25-500°C)	(10.5±0.5)x10 <sup>-6</sup> K <sup>-1</sup>
Accelerated aging surface monoclinic phase content	<10%
Chemical solubility after sintering	<100µg/cm <sup>2</sup>
Radioactivity	<0.1Bq/g
Sintering temperature	1530°C

## Chemical Composition

ZrO <sub>2</sub> + HfO <sub>2</sub> + Y <sub>2</sub> O <sub>3</sub>	>99%
Y <sub>2</sub> O <sub>3</sub>	4.4%-6%
Al <sub>2</sub> O <sub>3</sub>	<0.5%
Others oxides	<0.5%

Follow us on:

Upcera\_Official



upcera\_ \_official



UPCERA